



Description

Robex Plastic Membrane is a single pack high solids polymer coating for use as a flexible roof or wall coating.

Preparation

All surfaces should be clean and free from dust and grease. Any moss, lichen or algae should be removed using a fungicidal wash. All cracks and holes should be made good.

Mixing

N/A. Single pack, however, the product should be thoroughly stirred prior to use.

Curing Time

2-4 hours depending upon temperature and humidity.

Over-coating 8-12 hours.

Application

Apply by brush, roller or spray. A second coat should be applied after full cure of the first.

Minimum Cure Temperature

7°C (both air and substrate)

Coverage

2.25 - 3 sq mtrs per kg per coat.

Flash Point

N/A

Storage Life

12 months in original sealed containers.

Spraying Details

Do not thin product.

Equipment:	Graco King Pump
Air Supply:	100 c.f.m. Road Compressor
Tip Pressure:	1000 psi
Tip Size:	17 Thou
Spray Angle:	60°

General Notes

It should be remembered that porous surfaces will require a greater quantity of product than non-porous ones. In exceptional circumstances a third coat may be required.

Cleaning

To clean brushes, equipment, contaminants, etc., we recommend the use of **Robex All Purpose Cleaner**.

No liability is accepted for any injury, loss or damage arising directly or indirectly from the use of the Company's products or from the use of information given in our data sheets, since the customer's use of the product is necessarily out of our control. The information given is intended to serve as a guide only. Customers should satisfy themselves by appropriate trials that the products are suitable for their intended use.

Tel + 44 (0)1462 422 260

Fax: + 44 (0)1462 422 262

The Robex Group Wilbury Way HITCHIN Hertfordshire SG4 0TY United Kingdom www.robex.co.uk