

Robex RX2000 is a complex blend of resins reinforced with zinc phosphate and selected pigments. Developed to give a high level of protection on steel work it can be applied to the surface in wet or dry conditions.

Preparation

The surface to be painted must be clean and free from grease, dust, dirt, rust and other loose or flaking material. Prepare surface prior to application by either manual or mechanical methods with either rust scrapers, wire brush, chipping hammers, needle guns or blasting equipment.

Curing Time

Touch dry	2-4 hours. Re-coat if required after 12 hours
Hard dry	24 hours
Full cure	3-4 days

Application

RX2000 can be applied by brush, roller or air-less spray. The preferred method of application is by brush applying a heavy coat of 150 - 200 microns. For details regarding spraying please contact our Technical Department. Stir RX2000 thoroughly prior to application.

Minimum Cure Temperature

5°C

Flash Point

21 - 55°C

Coverage

4 - 6 sq metres per litre

Storage Life

24 months in original sealed containers, provided they are protected from frost and extremes of temperature.

Cleaning

To clean brushes, equipment, contaminants, etc., we recommend the use of **Robex All Purpose Cleaner**.

No liability is accepted for any injury, loss or damage arising directly or indirectly from the use of the Company's products or from the use of information given in our data sheets, since the customer's use of the product is necessarily out of our control. The information given is intended to serve as a guide only. Customers should satisfy themselves by appropriate trials that the products are suitable for their intended use.

Tel + 44 (0)1462 422 260

Fax: + 44 (0)1462 422 262

The Robex Group Wilbury Way HITCHIN Hertfordshire SG4 0TY United Kingdom www.robex.co.uk