



### **Description**

Robex Super Crete F.I.X. has been specially designed for large repairs to concrete achieving rapid strength quickly and can be used by pedestrians after only 2 hours and traffic after 4 hours.

### **Preparation**

All loose particles, laitance and contamination must be removed. Form buttress edges of at least 10 ml and pre-soak the area.

### **Priming**

For general repairs Super Crete will work without the use of a primer, however it is advisable to thoroughly soak the area with water. For large repairs & for use in areas subject to high wear we recommend applying a slurry as a primer. For information regarding using a slurry coat please contact our technical department.

### **Mixing Ratio**

Mixing can be carried out by hand drill paddle or standard tumble action machine. Add 2.75 to 3.00 litres of clean water and mix thoroughly with the Super Crete powder. This produces an easily workable stiff mortar consistency. Always add the powder to the water.

### **Pot Life (working life after mixing)**

45 minutes

### **Application Details**

Following thorough mixing of Super Crete F.I.X. apply as quickly as possible and firm well into position. When using a slurry coat apply whilst the slurry coat is still wet.

**When using in warm conditions it is advisable to cover the Super Crete or to 'spray' the surface with water to avoid curing too quickly which can result in de-bonding or small cracks appearing in the finished repair.**

### **Minimum Cure Temperature**

5°C

### **Coverage**

Depending on surface profile.

### **Shelf life**

6-9 months in good condition

No liability is accepted for any injury, loss or damage arising directly or indirectly from the use of the Company's products or from the use of information given in our data sheets, since the customer's use of the product is necessarily out of our control. The information given is intended to serve as a guide only. Customers should satisfy themselves by appropriate trials that the products are suitable for their intended use.

**Tel + 44 (0)1462 422 260**

**Fax: + 44 (0)1462 422 262**

The Robex Group Wilbury Way HITCHIN Hertfordshire SG4 0TY United Kingdom [www.robex.co.uk](http://www.robex.co.uk)